

ARME X ROOF ELASTO waterproofing membrane Technical Data Sheet

**Compound
SBS**

**Flexibility
-15**

rev. 05/2017

DESCRIPTION

ARME X ROOF ELASTO is a prefabricated modified polymer-bitumen membrane whose compound is composed of distilled bitumen and elastomers (SBS), having a special reinforcement made of **glass fiber fabric**, with excellent mechanical properties such as tensile strength and tear strength; furthermore the modified compound offers excellent ageing properties, cold flexibility, durability and a high elasticity.

These characteristics make it the ideal product for those applications which requires waterproofing membranes with great strength on mechanical fixing over the metal roofs.

ARME X ROOF ELASTO is available with a polyethylene film, sand or TNT (polypropylene mat) finish on the upper face to prevent the roll from sticking to itself and benefits the unrolling of the product during installation.

The lower face of **ARME X ROOF ELASTO** is backed by a special polyethylene burn-off film which melts during torching and prevents the roll from sticking to itself. The correct application temperature is visible from the lightly embossed surface of the membrane which is below the burn off film, when the correct application temperature is reached, this embossment melts also helping vapor diffusion and avoiding blistering.

AREA OF USE: base layer for multilayer applications in roof waterproofing, torch applied or mechanically fastened, especially recommendable over wood or metal decks with mineral wool insulation — by nail fixing

Technical properties	M.U.	ARME X ROOF ELASTO	Tolerances
Reinforcement		Glass fiber fabric	
Upper side finish	type	sand / polyethylene film / TNT	
Lower side finish	type	burn off polyethylene film	
Roll length (EN 1848-1)	m	10	± 0,2 %
Roll width (EN 1848 –1)	m	1	± 1 %
Nominal thickness (EN 1849 – 1)	mm	2 / 3	± 7 %
Cold flexibility (EN 1109)	°C	-15	-
Tensile strength (EN 12311-1)			
-longitudinal	N/ 5 cm	1200	± 20 %
-transversal		1200	
Ultimate elongation (EN 12311-1)			
-longitudinal	%	3	± 20 %.
-transversal		3	
Tear resistance (EN 12310 – 1)	N	350 / 350	± 20 %
Resistance to static loading (EN 12730)	kg	10	min
Dimensional stability (EN 1107 –1)	%	0,2	max
Flow resistance (EN 1110)	°C	120	min
Watertightness (EN 1928)	Kpa	60	min
Reaction to fire (EN 13501-1)	class	F	